

# 技術資料

## 11. 硬さ換算表

ロックウェル Cスケール硬さ H <sub>R</sub> C(荷重150kgf)	ピッカース 硬 さ H <sub>V</sub>	ブリネルかたさH <sub>B</sub> 10mm球, 荷重3000kgf		ロックウェル硬さ		シ 硬 さ H <sub>S</sub>	ヨ ア さ
		標 準 球	タングステン カーバイト球	H <sub>R</sub> A	H <sub>R</sub> B		
				Aスケール 荷重60kgf barle圧力	Bスケール 荷重100kgf 径1/16in球		
68	940	—	—	85.6	—	97	
67	900	—	—	85.0	—	95	
66	865	—	—	84.5	—	92	
65	832	—	739	83.9	—	91	
64	800	—	722	83.4	—	88	
63	772	—	705	82.8	—	87	
62	746	—	688	82.3	—	85	
61	720	—	670	81.8	—	83	
60	697	—	654	81.2	—	81	
59	674	—	634	80.7	—	80	
58	653	—	615	80.1	—	78	
57	633	—	595	79.6	—	76	
56	613	—	577	79.0	—	75	
55	595	—	560	78.5	—	74	
54	577	—	543	78.0	—	72	
53	560	—	525	77.4	—	71	
52	544	500	512	76.8	—	69	
51	528	487	496	76.3	—	68	
50	513	475	481	75.9	—	67	
49	498	464	469	75.2	—	66	
48	484	451	455	74.7	—	64	
47	471	442	443	74.1	—	63	
46	458	432	432	73.6	—	62	
45	446	421	421	73.1	—	60	
44	434	409	409	72.5	—	58	
43	423	400	400	72.0	—	57	
42	412	390	390	71.5	—	56	
41	402	381	381	70.9	—	55	
40	392	371	371	70.4	—	54	
39	382	362	362	69.9	—	52	
38	372	353	353	69.4	—	51	
37	363	344	344	68.9	—	50	
36	354	336	336	68.4	(109.0)	49	
35	345	327	327	67.9	(108.5)	48	
34	336	319	319	67.4	(108.0)	47	
33	327	311	311	66.8	(107.5)	46	
32	318	301	301	66.3	(107.0)	44	
31	310	294	294	65.8	(106.0)	43	
30	302	286	286	65.3	(105.5)	42	
29	294	279	279	64.7	(104.5)	41	
28	286	271	271	64.3	(104.0)	41	
27	279	264	264	63.8	(103.0)	40	
26	272	258	258	63.3	(102.5)	38	
25	266	253	253	62.8	(101.5)	38	
24	260	247	247	62.4	(101.0)	37	
23	254	243	243	62.0	100.0	36	
22	248	237	237	61.5	99.0	35	
21	243	231	231	61.0	98.5	35	
20	238	226	226	60.5	97.8	34	
(18)	230	219	219	—	96.7	33	
(16)	222	212	212	—	95.5	32	
(14)	213	203	203	—	93.9	31	
(12)	204	194	194	—	92.3	29	
(10)	196	187	187	—	90.7	28	
(8)	188	179	179	—	89.5	27	
(6)	180	171	171	—	87.1	26	
(4)	173	165	165	—	85.5	25	
(2)	166	158	158	—	83.5	24	
(0)	160	152	152	—	81.7	24	